

EMPOWERING

AGC

SOLAR EFFICIENCY

SOLAR

SOLAR THERMAL

SUN MIROX®

EXTRA CLEAR EXTRA THIN GLASS FOR PARABOLIC DISH AND PARABOLIC TROUGH COLLECTORS

パラボラディッシュ型、トラフ型太陽熱発電用の高透過・高反射薄板ガラス

SUN MIROX® is an extra clear extra thin high reflectivity mirror perfectly suited for lamination purposes and use in parabolic dish or parabolic trough collectors. Once laminated with an appropriate adhesive onto a support material the mirror is perfectly well protected and shows a very high chemical and mechanical durability.

SUN MIROX® conforms to EN1036. AGC can help you to select an appropriate adhesive in function of your support structure.

In order to minimize its environmental impact before, during and after service, SUN MIROX® is copper-free and lead-free

PRODUCT DESCRIPTION

Applications Parabolic dish or parabolic trough (laminated)

用途 太陽熱発電用集光ミラー (パラボラディッシュ型・トラフ型用)

集光ミラー用として最適な高透過・高反射の薄板ガラス。サポート資材への接着後、ミラーは化学的・機械的に非常に優れた耐久性を発揮。

SUN MIROX®は、欧州統一規格EN1036に準拠。ミラーのサポート構造に合わせた最適な接着方法が選択可能。環境影響を最小化するため銅・鉛を使用していません。



ASAHI GLASS CO., LTD.

Shinyurakucho bldg., 1-12-1 Yurakucho, Chiyoda-ku, Tokyo 100-8405 JAPAN Phone: +81 3 3218 7774 Fax: +81 3 3218 7008

E-mail: sales.asia@jp.agc-solar.com URL: <http://www.agc-solar.com>

旭硝子株式会社 〒100-8405 東京都千代田区有楽町1-12-1 新有楽町ビル 8

WORLDWIDE

Chaussée de La Hulpe, 166 1170 Brussels Belgium Phone: +32 2 674 34 01 Fax: +32 2 674 31 22 E-mail: sales@agc-solar.com

MAIN CHARACTERISTICS *

Energy reflectivity (%)	0.95mm: 95.1	ISO 9050 AM1.5
	1.25mm: 94.8	ISO 9050 AM1.5
Minimum curvature (m)	0.95mm: 3.5	Based on 10MPa as design stress
	1.25mm: 4.6	Based on 10MPa as design stress
Specific weight (kg/m ²)	0.95mm: 2.4	
	1.25mm: 3.1	
Typical length	From 150mm to 3210mm	
Typical width	From 150mm to 1580mm	
	Other dimensions available on request.	

AGC can help evaluating these values according to other standards and/or to the specificities of the final application.

DURABILITY TESTS *

Humid chamber	Passed (not laminated)	EN1036
Neutral salt spray	Passed (not laminated)	ISO 9227
CASS	Passed (not laminated)	ISO 9227
Thermal cycling	Passed (not laminated)	From -20°C to +75°C, up to 100% RH
Weather O Meter	Passed (not laminated)	Combination of light, temperature and water
UV resistance	Passed (laminated)	UVA 340 at 60°C, 39W/m ²

MECHANICAL CHARACTERISTICS - NOT LAMINATED *

Mechanical strength (MPa)	45	Annealed
Young modulus (GPa)	70	EN572
Poisson ratio	0.2	EN572
Hardness Moh (scratch hardness) 6 EN572		
Knoop (indentation hardness)	470	Indenter load 500g
Density (kg/m ³)	2500	EN572, at 18°C

THERMAL CHARACTERISTICS *

Hemispherical emissivity	0.84	Between -18°C and 66°C
Expansion coefficient (10 ⁻⁶ 1/K)	9	EN572, between 20°C and 300°C
Specific heat (J/kg/K)	720	EN572
Thermal conductivity (W/m/K)	1	EN572
Softening point (°C)	722	
Annealing point (°C)	552	
Strain point (°C)	500	

CHEMICAL COMPOSITION *

Silicon dioxide (SiO ₂ , %)	69 to 74	EN572
Sodium oxide (NaO, %)	12 to 16	EN572
Calcium oxide (CaO, %)	5 to 12	EN572
Magnesium oxide (MgO, %)	0 to 6	EN572
Aluminium oxide (Al ₂ O ₃ , %)	0 to 3	EN572
Trace elements (FeO, etc., %)	<1	

AGC is committed to environmental stewardship through the use of recyclable materials and sustainable process in the manufacturing and distribution of our state-of-the-art, energy efficient flat glass products.

In North America, the product performs to the appropriate ASTM standards.

*The information contained in this datasheet is intended to assist you in designing with AGC materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose. The user is responsible for determining the suitability of AGC materials for each applications.

FOR MORE INFORMATION

Worldwide: sales@agc-solar.com

Europe: sales.europe@eu.agc-solar.com

North America: sales.northamerica@na.agc-solar.com